



**RANGAN FAR CO.**  
MANUFACTURER OF INDUSTRIAL PAINTS

FARCO INTER 566

## M.I.O CHLORINATED RUBBER INTERMEDIAT COAT

### PRODUCT INFORMATION

- 1-Suitable for interior and exterior use.
- 2-Fast drying.
- 3-Resistant to salt water, splashes of mineral oils, aliphatic Solvents, petrol, and a wide range of chemicals but not to Animal and vegetable oils or aromatic solvents.
- 4- Good abrasion resistance

### Physical data

Colour:	Grey
Finish:	Flat
Flash point:	24 °C
Volume solids:	52 ±5%
D.f.t:	50-70 microns
Specific gravity:	1.5 ± 0.08gr/cm <sup>3</sup>
Theoretical coverage:	10.4 m <sup>2</sup> /lit (at 50 µ d.f.t)
Drying time at 25°C:	
touch dry:	1 hr
dry to handle:	3 hrs
full cure:	72 hrs
Component:	1
Application methods:	Conventional spray or brush or airless spray or roller
Recoat intervals* :	10 °C          25 °C          40 °C
(mild condition) : Min:	6 hrs          2 hrs          1 hrs
Max:	24 hrs          10 hrs          6 hrs
Recommended thinner:	FARCO THINN 56
Recommended cleaner:	FARCO CLEAN 56
Curing mechanism:	by solvent release
Substrate:	Steel and primed steel

\*: For recoating the surface should be free of dust ,grease and contamination

**R**  
**A**  
**N**  
**G**  
**A**  
**N**  
  
**F**  
**A**  
**R**



## Typical uses

As a primer and intermediate coat for steel,galvanized steel.

Other uses are:

Ships hulls, decks and super structures,offshore structures and piping in chemical plants,refineries, pulp and paper mills, bridges and cranes

## Application information

This Rangan Far's product is a m.i.o chlorinated rubber primer or intermediate coat for immersion and nonimmersion systems.to obtain the maximum performance for which this product is formulated, strict adherence to all application , instructions. precautions, conditions and limitations is necessary.

## Application equipment

The following equipment is listed as a guide and suitable equipment from other manufactures may be used.

Adjustments of pressure and change of tip size may be needed to obtain the proper spray characteristics.

1-Airless spray:standard airless spray equipment having A 28:1 or higher pump ratio and a fluid tip with a 0.457 to 0.660 mm Orifice.

2-Conventional spray:industrial equipment with suitable aircap having a fluid tip with A 2- 2.2 mm orifice .

3-Brush/roller.

4- Mixer

## Caution

1-Keep away from heat and open flame.

2-Keep containers closed.

3-Use with adequate ventilation.

4-Avoid prolonged and repeated contact with skin.

**R**  
**A**  
**N**  
**G**  
**A**  
**N**  
**F**  
**A**  
**R**





5-Use fresh air masks and explosion proof equipment.

6-Take precautionary measures against static discharges.

### **Application procedure**

1-Flush equipment with recommended cleaner before use.

2-Stir all material thoroughly before applying.

3-Thinning with thinner as needed for workability.

4- Apply a wet coat by even, parallel passes. overlap each pass 50% to avoid bare areas, pinholes or holidays. small damaged or bare areas and random pinholes or holidays can be repaired by simply applying additional material.

5-In confined areas ventilate with clean air during application and drying until all solvents are removed.

Temperature and humidity of ventilating air must be such that moisture condensation will not form on surface.

6-Clean all equipment with recommended cleaner immediately after use.

### **Environmental condition**

Environmental temperature must be 10-40°C.

Surface temperature must be at least 3°C above dew point to prevent condensation. At freezing temperature surface must be free of ice and relative humidity below 80 %.

### **Surface preparation**

Blasting to a standard of Sa 2.5 – Sa3 , SIS 05 5900 , ISO 8501-1.

**R  
A  
N  
G  
A  
N  
  
F  
A  
R**